

Trademark	Emsodur GV
Manufacturer	Emsodur AG Industriepark Vial 2 CH-7013 Domat/Ems Tel.: +41 81 632 80 11
Colour	as per product code
Shape	cubic, cylindrical (as per product code)
Dimension	0.75mm 1.00mm 1.50mm
Storage stability	unlimited, when stored in a cool and dry place

Physical characteristics

Density	1.30-1.40 g/cm ³
Bulk density	0.60-0.80 kg/l (depending on dimension)
Hardness	83 Shore-D 110 Rockwell 3 Mohs
Water absorption	3 % (23°C/50 % r.F. ISO 62)

Chemical characteristics

Composition	Polyamide 6, Additive
pH-value at 250 g/l H ₂ O, 20°C	-
Ash content	-

Thermic characteristics

Flash point	-
Melting point	215 – 225 °C
Boiling point	-